



N-type TOPCon Solar cell


NG1218D2



Front side



Rear side



Low hot spot effect



High efficiency with high reliability



Excellent uniformity of cell performance and stability of process



Excellent power generation performance under low irradiation



No LID/LeTID



Bifacial benefits



Cell to Module with high matching rate

Product Features

Product Model:	NG1218D2
Dimension:	210mmx210mm±0.5mm
Cell Thickness:	130μm±13μm
Front side:	0.03±0.015mm wide bus bars, Silicon nitride, aluminum oxide
Back side:	0.03±0.015mm wide bus bars, Silicon nitride

Electric Performance

Efficiency(%)	Power Pmpp(W)	Max.Power Current Impp(A)	Short Circuit Current Isc(A)	Max.Power Voltage Vmpp(V)	Open Circuit Voltage Voc(V)
25.5	11.24	18.17	18.24	0.619	0.720
25.4	11.20	18.13	18.21	0.618	0.719
25.3	11.16	18.08	18.19	0.617	0.718
25.2	11.11	18.04	18.16	0.616	0.717
25.1	11.07	17.99	18.13	0.615	0.716
25.0	11.02	17.95	18.10	0.614	0.715
24.9	10.98	17.90	18.07	0.613	0.714
24.8	10.94	17.86	18.04	0.612	0.713
24.7	10.89	17.81	18.01	0.612	0.712
24.6	10.85	17.77	17.98	0.611	0.712
24.5	10.80	17.72	17.95	0.610	0.711
24.4	10.76	17.67	17.93	0.609	0.710
24.3	10.72	17.63	17.90	0.608	0.709
24.2	10.67	17.58	17.87	0.607	0.708
24.1	10.63	17.54	17.84	0.606	0.707
24.0	10.58	17.49	17.81	0.605	0.706

- Under standard test condition: 1000W/ m², AM 1.5G, 25°C
- Illustration: 25.0%
- Specifications and data are provided for reference only

Temperature Coefficients

Current Temperature Coefficient	Tkcurrent: +0.045%/K
Voltage Temperature Coefficient	Tkvoltage: -0.25 %/K
Power Temperature Coefficient	Tkpower: -0.29%/K

